

Closure mortar



Ready-to-use cement-based dry mix for filling cone/anchor holes. Grain size 0-4 mm.

Controlled volumisation during the setting process.
High early and very high final strength
Water-impermeable

Consumption

Consumption:

One bag yields 13 litres of sealing mortar
Cone EX in combination with FLUPP: per bag approx. 500 holes
Cone EX holes, e.g. EX 22/10 and EX FB: per bag approx. 1200 holes
MKK® BETOMAX® 15 cone holes: per bag approx. 60 holes
Pipe spreaders 22: per bag approx. 30 metres of pipe spreaders (inner Ø 22), e.g. Dist K-22 rough

Processing

Processing:

Depending on the size of the cone hole, between 14 % and 18 % water, i.e. approx. 3.5 l - 4.5 l per 25 kg dry mortar.
Mix the full quantity of dry mortar with 2/3 of the water quantity.
Add remaining water during the mixing process.
Mixing time approx. 4 minutes
Working temperature from 5°C

Article description	Title of variant	Packaging piece/pallet	Weight kg/piece
19025000	Closure mortar	1-42 bag/pallet	25